

## Europäisches Patentamt European Patent Office Office européen des brevets

EP 1 445 812 A1

(12)

## EUROPEAN PATENT APPLICATION published in accordance with Art. 158(3) EPC

(43) Date of publication: 11.08.2004 Bulletin 2004/33

(21) Application number: 02801572.5

(22) Date of filing: 15.10.2002

(51) Int CI.<sup>7</sup>: **H01M 6/08**, H01M 4/52, H01M 4/62, H01M 4/66, H01M 10/30

(86) International application number: PCT/JP2002/010683

(11)

(87) International publication number: WO 2003/034520 (24.04.2003 Gazette 2003/17)

- (84) Designated Contracting States:

  AT BE BG CH CY CZ DE DK EE ES FI FR GB GR
  IE IT LI LU MC NL PT SE SK TR
- (30) Priority: 17.10.2001 JP 2001319855 17.10.2001 JP 2001319857 17.10.2001 JP 2001319858
- (71) Applicant: Sony Corporation Tokyo 141-0001 (JP)
- (72) Inventors:
  - TAKAHASHI, Akio, c/o SONY FUKUSHIMA CORPORATION Koriyama-shi, Fukushima 963-0531 (JP)
  - MORIKAWA, Shinichiro, c/o SONY CORPORATION Tokyo 141-0001 (JP)

- HAYASHI, Naoki, c/o SONY CORPORATION Tokyo 141-0001 (JP)
- HONDA, Kazuo, c/o SONY FUKUSHIMA CORPORATION Koriyama-shi, Fukushima 963-0531 (JP)
- OYA, Kuniyasu,
   c/o SONY FUKUSHIMA CORPORATION
   Koriyama-shi, Fukushima 963-0531 (JP)
- YAMAMOTO, Kenta, c/o SONY CORPORATION Tokyo 141-0001 (JP)
- KOBAYASHI, Noriyuki, SONY FUKUSHIMA CORPORATION Koriyama-shi, Fukushima 963-0531 (JP)
- (74) Representative: Müller Hoffmann & Partner Patentanwälte, Innere Wiener Strasse 17 81667 München (DE)

## (54) ALKALINE BATTERY

(57) The present invention provides an alkaline battery suitable for use as a primary or secondary battery as a power source of electronic appliances. The battery is excellent in discharge characteristics under a heavy load and in cycle characteristics.

The alkaline battery (100) comprises a cathode mix (3) containing  $\beta$ -nickel oxy-hydroxide, an anode mix (5) containing zinc as a main component of anode active material, and an alkali solution as an electrolyte, wherein the cathode mix (3) includes a mixture of  $\beta$ -nickel oxy-hydroxide, graphite powder, and a potassium hydroxide solution in a given weight ratio. The  $\beta$ -nickel oxy-hydroxide is prepared by chemical oxidation and has an approximately spherical shape of particle with a mean particle size in the range of 5 to 50  $\mu$ m.

FIG. 3

DISCHARGE TIME CURVE OF B-HIOOH PREPARED BY CHEMICAL OXIDATION
TO ISCHARGE TIME CURVE OF y-HIOOH PREPARED BY CHEMICAL OXIDATION

